Central Coast Testing

290 Ridge Road Ben Lomond, CA 95005 831.429.8447 (voice) 831.423.8450 (fax)

Bariatric Wheelchair Seat Cushion Testing Report - Increased Load to 350 Pound User - Simulated Use Increased to 36 Months

CUSHION INFORMATION

Manufacturer	Action Products	Manufacture Date	January 2005
Manufacturer's Lot #	076RX	Serial Number	XS2020
Product Line Name	XACT	Model Name So	ft
Maximum recommend	led user weight (kg) 159.1 (350	lb)	
HCPCS Seat Cushion	Code E2607 Skin Protection and	d Positioning Cushio	n

CUSHION DIMENSIONS

Width (cm)	50.8 (20 in)	Length (cm)	50.8 (20 in)
Thickness (cm)	13.0 (5.2 in)	Weight (lbs)	5.3 lbs

METHODOLOGY

Loaded Contour testing and structural characteristic assessment were conducted according to the DMERC – Local Medical Review Policy – Final – Wheelchair Seating, Spring 2004¹. Simulation testing was modified following guidelines under development within the ISO 16840 working group that is developing Wheelchair Seating Standards. In this test a 20-inch wide LCJ indenter was used for loaded contour testing. In addition, the simulated use testing incorporated a 20-inch wide RCLI indenter that was loaded to represent a 350 pound user.

CLI used _40 mm Date(s) of tests _25 February/1 March 2005

RESULTS- SUMMARIZED

Prior to simulated use testing:	
Loaded contour depth test	🗹 PASSED
Overload test for measuring bottoming out	🗹 PASSED
After simulated use testing:	
Loaded contour depth test	🗹 PASSED
Overload test for measuring bottoming out	☑ PASSED

Simulation tests demonstrated a loaded contour depth of at least 40 mm with an overload deflection of at least 5 mm. Following testing simulating 36 months of use at an increased load, simulation tests demonstrated a loaded contour depth of at least 40 mm with an overload deflection of at least 5 mm.

Positioning cushions minimum structural characteristics assessment .. 🗹 PASSED 🛛 FAILED 🔅 N/A

Report prepared by:

06 March 2005

Allen Siekman, Testing Supervisor

RESULTS- DETAILED

Positioning Cushion Structural Characteristics

The positioning cushion exhibited the following structural characteristic(s):

Two lateral pelvic supports A medial thigh support Two lateral thigh supports

* If the cushion is coded as E2605, E2606, E2607, and E2608 and has two or more structural characteristics or two or more air compartments, then the cushion is determined to have passed the structural characteristic assessment.

Cushion Loading Indenters

A 20-inch wide Loaded Contour Jig (LCJ) cushion-loading indenter (CLI) was used to test the cushion. In this test, the LCJ met the specific design features of acceptable CLIs as developed by the ISO working group developing Wheelchair Seating Standard ISO 16840. The results obtained with the LCJ are reported in the *Summary of Results* on page 1.

Results – Prior to Simulated Use	Test Date:	02/25/2005

 Testing room conditions:
 Temperature (F)
 68
 Relative Humidity (%)
 58%

Loaded Contour Depth with LCJ indenter	Test #1	Test #2	Test #3	Result
Lateral buttons of the CLI contacted the cushion when loaded to 140 N (31 lb)	Yes	Yes	Yes	Pass

Overload Test with LCJ indenter	Test #1	Test #2	Test #3	Result
1) Height of CLI when loaded to 140 N (31 lb) (standard load) (mm)	59.88	57.73	57.38	
 Height of CLI when loaded to 187 N (41 lb) (overload) (mm) 	55.18	53.73	53.49	
 Height at standard load (#1) minus height at overload (#2) (mm) 	4.7	4.0	3.89	
 Value in #3 rounded to the nearest 5 mm (mm) 	5	5	5	
5) Overload deflection* (mm) (median of the 3 values in #4)				5 Pass

* If the overload deflection is greater than or equal to 5 mm, then the cushion is determined not to have bottomed out during the test.

Simulated Use Procedure

Test Date: 02/25/2005

To simulate cushion use, the test cushion was subjected to cyclic loading in a heated chamber. In this test, the cushion was subjected to 18 months of simulated use, tested for load and overload and then subjected to an additional 18 months of use and retested for load and overload. For each simulated use

test, the test cushion was preconditioned for 30 minutes in a test chamber maintained at 70 ±2 degrees C. The test cushion was then loaded to 1092 ±10 Newtons for 22,000 cycles for each 18 month simulated use cycle. The cushion was loaded with the increased load at a rate of 30 times per minute using the RCLI in the test chamber maintained at 70 ±2 degrees C.

The number of cycles was determined as follows:

For testing simulating 18 months of use:

40 pressure reliefs per day x 30 days per month x 18 months x RF \approx 11,000 cycles where RF = 0.5, the reduction factor for testing at an elevated temperature.

This cushion was tested to a total of **44,000** cycles.

Cushion Preconditioning Time	0800 hrs	_ Test chamber temperature (deg C)	70
------------------------------	----------	------------------------------------	----

Time test started 0830 hrs

Results – After 18 Months of Simulated Use Test Date: 02/28/2005

Testing room conditions: Temperature (C) 20.0 Relative Humidity (%) 43

Loaded Contour Depth with LCJ indenter	Test #1	Test #2	Test #3	Result
Lateral buttons of the CLI contacted the cushion when loaded to 140 N (31 lb)	Yes	Yes	Yes	Pass

Overload Test with LCJ indenter	Test #1	Test #2	Test #3	Result
1) Height of CLI when loaded to 140 N (31 lb) (standard load) (mm)	56.10	54.50	52.13	
2) Height of CLI when loaded to 187 N (41 lb) (overload) (mm)	50.40	49.72	47.74	
 Height at standard load (#1) minus height at overload (#2) (mm) 	5.7	4.78	4.39	
4) Value in #3 rounded to the nearest 5 mm (mm)	5	5	5	
5) Overload deflection* (mm) (median of the 3 values in #4)				5 Pass

• If the overload deflection is greater than or equal to 5 mm, then the cushion is determined not to have bottomed out during the test.

Simulated Use to 36 Months

Cushion Preconditioning Time	2050 hrs	Test chamber temperature (deg C)	70
Time test started	2100 hrs	Date: 28 February 2005	

2A0A7017B7FBE65585256D1E0044C7BB?OpenDocument

Central Coast Testing	104-02 Action RPT.doc	rev: 2/7/2005

Overload Test with LCJ indenter	Test #1	Test #2	Test #3	Result
1) Height of CLI when loaded to 140 N (31 lb) (standard load) (mm)	59.92	56.47	55.58	
2) Height of CLI when loaded to 187 N (41 lb) (overload) (mm)	53.50	51.57	50.97	
 Height at standard load (#1) minus height at overload (#2) (mm) 	5.42	4.90	4.61	
4) Value in #3 rounded to the nearest 5 mm (mm)	5	5	5	
5) Overload deflection* (mm) (median of the 3 values in #4)				5 Pass

COMMENTS

This testing protocol subjected the test cushion to loads over twice as great as the standard testing specified in the DMERC testing policy. In addition, the increased duration of the simulated use test (36 months) is double the required amount. Testing the cushion in this manner assures that the cushion far exceeds the performance requirements outlined in the standard cushion testing protocol. This may be a significant factor when using the cushion for Bariatric clients.

At the 18 months testing cycle, there was a separation of the waterproof film between the rear vertical edge at the bottom rear of the cushion. The film was not torn at other locations, and would likely maintain the waterproof properties in the areas of user contact. Cushion performance was not affected. The tear was 274 mm long, approximately centered on the rear of the cushion.

DMERC – Local Medical Review Policy – Final – Wheelchair Seating, Spring 2004 (n.d.). Retrieved March 18,

2004, from Palmetto GBA Web site: http://www.palmettogba.com/palmetto/lmrps_dmerc.nsf/final/

Results – After 36 Months of Simulated Use Test Date: 03/01/2005

Test #1

Yes

Test #2

Yes

Testing room conditions: Temperature (C) 20.0 Rela

Loaded Contour Depth with LCJ indenter

Lateral buttons of the CLI contacted the

cushion when loaded to 140 N (31 lb)

Relative Humidity (%) 53

Result

Pass

Test #3

Yes